In the Claims

The following listing of the claims replaces all previous listings.

- 1.-29. (Canceled)
- (Currently Amended) A compression molding composition for use in compression 30. molding an article, said composition comprising:

an inorganic fiber, an inorganic binder, a carrier solvent, and additional additives, wherein at least a portion of the inorganic binder is suspended in at least a portion of the carrier solvent;

wherein the composition is in the range of greater than 0 to less than or equal to about 25 % by wt. inorganic fiber;

wherein the composition is in the range of about 1915 to 4935 % by wt. inorganic binder suspended in an aqueous solution;

wherein the composition is in the range of about 15 to 45 % by wt. carrier solvent; and wherein the composition is in the range of about 0 to 70 % by wt. additional additives.

- 31. (Canceled)
- 32. (Previously Presented) The composition of claim 30, wherein the additional additives include an inorganic filler, and the inorganic filler is in the range of 15 to 70 % by weight of the total composition.
- (Previously Presented) The composition of claim 30, wherein the additional additives 33. include an organic polymer, and the organic polymer is in the range of 0.1 to 0.5 % by weight of the total composition.
- 34. (Original) The composition of claim 33, wherein the organic polymer is an acrylic polymer.

- 6123329081
- (Previously Presented) The composition of claim 33, wherein the organic polymer acts 35. as a molding thickener to help the composition hold shape when it is being molded.
- (Original) The composition of claim 30, wherein the carrier solvent is water. 36.
- 37. (Original) The composition of claim 36, wherein the composition has a moisture content in the range of 20 to 35% by weight of the total composition.
- 38. (Original) The composition of claim 37, wherein the composition has a moisture content 23 to 30% by weight of the total composition.
- 39. (Original) The composition of claim 38, wherein the composition has a moisture content in the range of 25 to 27% by weight of the total composition.
- (Previously Presented) The composition of claim 30, wherein the inorganic binder is 40. colloidal silica.

This Page is Inserted by IFW Indexing and Scanning Operations and is not part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

| BLACK BORDERS
| IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
| FADED TEXT OR DRAWING
| BLURRED OR ILLEGIBLE TEXT OR DRAWING
| SKEWED/SLANTED IMAGES
| COLOR OR BLACK AND WHITE PHOTOGRAPHS
| GRAY SCALE DOCUMENTS
| LINES OR MARKS ON ORIGINAL DOCUMENT
| REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY

IMAGES ARE BEST AVAILABLE COPY.

OTHER:

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.